



Data Sheet for:

Graphite Gasket Material

Specification	Test Method	Value		
Grade	-	JAH 1000 HOMOGENOUS	JAH 1200 STAINLESS STEEL FOIL	JAH 1100 STAINLESS STEEL TANGED
Thickness	-	0.25mm, 0.35mm, 0.4mm, 0.5mm, 0.8mm, 1.0mm, 1.5mm, 2.0mm, 3.0mm	0.75mm, 1.0mm, 1.5mm, 2.0mm, 3.0mm	1.0mm, 1.5mm, 2.0mm, 3.0mm
Temperature Range				
Intermittent dry	-	-200°C to +500°C	-200°C to +500°C	-200°C to +500°C
Intermittent steam	-	-200°C to +650°C	-200°C to +650°C	-200°C to +650°C
Maximum Pressure	-	40 bar	140 bar	140 bar
Density	-	1.1g/cm ³	1.1g/cm ³	1.1g/cm ³
Ash Content	DIN 51 903	<1.0%	<1.0%	<1.0%
Leachable Chloride Content	-	<50ppm	<50ppm	<50ppm
Material of Insertion	DIN/ASTM	-	1.4401/SS (foil)	1.4401/SS (tanged)
Thickness of Insertion	-	-	0.05mm	0.1mm
Number of Inserts	-	-	1 or 2	1 or 2
Gas Permeability	-	<0.30, <0.60, <0.80, <0.80 (cm ² /min)	<0.60cm ² /min	<0.60, <0.60, <0.80, <1.0 (cm ² /min)
Spec. Leak Pate	-	<0.05, <0.08, <0.1, <0.1 (mg/s/n)	-	-
Stress Relaxation	DIN 52 913, 16hrs @ 300°C	<47mg/s/n	>45mg/s/n	>48, >48, >48, >45 (mg/s/n)
Compressibility	ASTM F 36A-66	40 - 50%	40 - 50%	30 - 35%, 30 - 35%, 30 - 40%, 30 - 40%
Recovery	ASTM F 36A-66	10 - 15%	10 - 15%	15 - 20%
Minimum Gasket Assembly Stress	-	20N/mm ²	10N/mm ²	20N/mm ²
M Din Factor	-	1.3	1.3	1.3
Maximum Permissible Gasket Stress	-	160, 140, 120, 120 (N/mm ²)	100N/mm ²	180, 160, 140, 120 (N/mm ²)
Maximum	-	140, 120, 100,	100N/mm ²	160, 140, 120,

Oliver Ashworth Limited

Permissible Gasket stress (under service conditions)	-	100 (N/mm ²)		100 (N/mm ²)
M ASTM Factor	-	2	3	3, 3, 2.5, 2.5
Y PSI ASTM Factor	-	1500	900	9000, 9000, 4000, 4000

Disclaimer: While care has been taken to ensure the information contained in this publication is correct, Oliver Ashworth Limited accepts no responsibility or liability for information found to be misleading. Technical information has been supplied by our supply chain partners. It is the responsibility of the end-user to ensure that the products used are suitable for their intended application.

**Ashworth, Mill Hill Street, Bolton, Greater Manchester, BL2 2AB,
Tel: 0161 967 0400**

Enquiries@Ashworth.uk.com

Technical.services@Ashworth.uk.com